

## Resistance of ipPORE track-etched membrane filters to ACIDS and BASES

	polycarbonate	polyester	polyimide
Acetic Acid, 5%	R	R	R
Acetic Acid, 10%	R	R	R
Acetic Acid, Glacial	LR	R	R
Boric Acid	R	R	R
Hydrochloric, 6N	R	LR	T
Hydrochloric, Conc.	R	NR	T
Hydrofluoric, 10%	R	R	T
Hydrofluoric, 35%	R	R	T
Nitric Acid, 6N	R	R	T
Nitric Acid, Conc.	R	NR	T
Sulphuric Acid, 6N	R	R	T
Sulphuric Acid, Conc.	NR	NR	T
Ammonium Hydroxide, 6N	NR	LR	NR
Potassium Hydroxide, 6N	NR	NR	NR
Sodium Hydroxide, 6N	<b>NR</b>	<b>LR</b>	<b>NR</b>

R = recommended

LR = limited resistance

NR = not recommended

T = to be tested