

Resistance of ipPORE track-etched membrane filters to SOLVENTS

| | polycarbonate | polyester | polyimide |
|---------------------------|---------------|-----------|-----------|
| Acetone | LR | R | R |
| Acetonitrile | LR | R | R |
| Amyl Acetate | R | R | R |
| Aniline | NR | R | R |
| Benzene | LR | R | R |
| Bromoform | NR | R | R |
| Butyl Acetate | R | R | R |
| Carbon Tetrachloride | LR | R | R |
| Chloroform | NR | R | R |
| Cyclohexane | R | R | R |
| Cyclohexanone | LR | R | R |
| Diethyl Acetamide | LR | R | R |
| Dimethyl Formamide | NR | R | R |
| Dimethyl Sulfoxide (DMSO) | NR | R | R |
| Dioxane | NR | R | R |
| Ethyl Ether | R | R | R |
| Ethylene Dichloride | NR | R | R |
| Formaldehyde | R | R | R |
| Hexane | R | R | R |
| Isopropyl Acetate | R | R | R |
| Methyl Acetate | NR | R | R |
| Methyl Ethyl Ketone | LR | R | R |
| Methyl Isobutyl Ketone | LR | T | R |
| Methylene Chloride | NR | R | R |
| Nitrobenzene | NR | R | R |
| Pentane | R | R | R |
| Perchloroethylene | R | T | R |
| Pyridine | NR | R | R |
| Tetrahydrofuran | NR | R | R |
| Toluene | LR | R | R |
| Trichloroethane | NR | T | R |
| Trichlorethylene | NR | R | R |
| Triethylamine | LR | R | R |
| Xylene | NR | R | R |

R = recommended

LR = limited resistance

NR = not recommended

T = to be tested